LAPOX® AH-341



Technical Data Sheet | Polymers Business

Description

Lapox AH-341 is a modified aliphatic amine having low viscosity and light colour. It is recommended for high solid and solvent free coatings. It has got excellent resistance to amine blushing under humid conditions. Due to low viscosity it is capable of high filler loading and good wetting properties. This hardener offers better area coverage, long working time with good glossy films.

Advantages

Excellent resistance to amine blush

Free from amine blush

Glossy finish Long working time

Applications

Solvent free high solid coatings

Processing

Brush, roller or spray coating

Typical specifications

| Properties | Unit | Test method | Values |
|-------------------|----------|-------------|--------------|
| Appearance | - | Visual | Clear liquid |
| Colour | GS | ASTM D1544 | Max 2 |
| Amine value | mg KOH/g | ASTM D2073 | 290 - 320 |
| Viscosity at 25°C | m Pas | ASTM D2196 | 30 - 100 |
| Pot life at 25°C1 | Minutes | ASTM D2471 | 100 - 120 |
| AHEW | g/eq | - | 76 |
| Recommended ratio | w/w | - | 40 |

¹Pot life of 100 g mix mass. Mixing ratio with Lapox B-11 (EEW 190): Lapox AH-341 is 100:40 w/w

Packaging

Lapox AH-341 is available in 200 kg MS | HDPE drums and 1,000 kg IBC. Other packing may be considered on request.

Storage and handling

Lapox AH-341 should be stored in a cool and dry place, preferably in a sealed container and should not be exposed to direct sunlight. This product has a shelf-life of 1 year, if stored in its original container between 18°C and 25°C away from humidity and excessive heat. Please refer to the Safety Data Sheet (SDS) for detailed instructions on storage and handling.

Safety

Wear personal protective equipment (PPE). Avoid contact with the eyes and skin. In case of direct contact and irritation, the resin should be washed off immediately with soap and warm water. Avoid breathing vapours, mist or gas. Please refer to the SDS for detailed safety instructions.

Spills and disposal

In case of spills, sweep up and shovel the spilled material. Keep spilled material in suitable, closed containers for disposal. Soak up with an absorbent such as clay, sand or other suitable material. Flush area with water to remove trace residue. Do not allow the product to reach the sewage system. Waste must be disposed of in accordance with federal, state or local regulations, as applicable.

February 2018 Page 1 of 2

LAPOX® AH-341



Technical Data Sheet | Polymers Business

Contact E-mail: polymers@atul.co.in

Website: www.atul.co.in

Note Lapox[®] is a registered trademark of Atul Ltd.

Manufacturing site

Atul 396 020, Gujarat, India

Telephone: (+91 2632) 230000 | 233261

E-mail: contact@atul.co.in

Disclaimer: The information contained herein is for information purposes only. While enough care is taken in disclosing the information, users of this information are advised to cross-check the same depending upon use | application. Atul Ltd does not give any assurance or warranty or guarantee in regard to the accuracy or completeness of the information and no claim or liability will be accepted or entertained in regard thereto. Atul Ltd makes no warranty of any kind, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose or performance or usage of trade.

February 2018 Page 2 of 2