

LAPOX[®] ARL-125 | AH-336

Technical Data Sheet | Polymers Business



Ambient cure epoxy system for Infusion

Lapox ARL-125	100	pbw
Lapox AH-336	32	pbw

Description

Lapox ARL-125 is a modified epoxy laminating resin, designed for high performance applications and Lapox AH-336 is a modified polyamine based hardener suitable for high mechanical performance applications in static and dynamic load conditions. The moderate initial viscosity of this system ensures fast and complete impregnation of reinforcing fibers such as glass, carbon and polyamide. It allows components to be produced by various process techniques with high consistency in performance properties. The components cured at room temperature provides an excellent handling strength. The optimum properties, however, will only be obtained after post curing at temperature of more than 50°C. Fully cured components prepared by this system are recommended to operate between -60°C and 80°C temperature.

Applications

Automotive
Electrical
Gliders
Motor gliders and planes
Moulds and tools
Other industrial and house hold components
Recreational and sporting goods
Ships and boats
Wind turbine blades

Processing

Contact pressure mouldings
Filament winding
Pultrusion
Resin infusion (RI)
Resin transfer moulding (RTM)
Vacuum and pressure bag techniques
Wet lay-up lamination

Typical specifications

Lapox ARL-125

Properties	Unit	Test method	Values
Appearance	-	Visual	Clear liquid
Colour	GS	ASTM D1544	Max 2
Density at 25°C	g/cm ³	ISO 1183	1.1 - 1.2
Viscosity at 25°C	m Pas	ASTM D2196	1,000 - 1,500
Epoxy value	Eq/kg	ASTM D1652	5.40 – 6.02

Lapox AH-336

Properties	Unit	Test method	Values
Appearance	-	Visual	Clear liquid
Colour	GS	ASTM D1544	Max 4
Viscosity at 25°C	m Pas	ASTM D2196	20 - 100
Density at 25°C	g/cm ³	ISO 1183	0.93 - 0.99

Processing properties

Properties	Unit	Test method	Values
Mixing ratio (by weight)	-	Visual	Resin: 100 Hardener: 32
Initial mix viscosity	m Pas	ASTM D2196	400 - 650 / 25°C
Pot life	Minutes	ASTM D2471	120 - 160 at 20°C 80 - 100 at 25°C
Curing shrinkage	%	-	1.5
Curing schedule	°C / hours	-	25°C / 24 hours + 70°C / 8 hours

Typical properties of neat cured system

Curing schedule: 25°C / 24 hours + 70°C / 8 hours
Determined on standard test specimen at 25°C

Properties	Unit	Test method	Values
Tensile strength	MPa	ISO 527	60 - 70
Elongation at break	%	ISO 527	4 - 7
Elastic modulus in tension	GPa	ISO 527	2.8 - 3.4
Flexural strength	MPa	ISO 178	115 - 130
Elastic modulus in flexural	GPa	ISO 178	3.0 - 3.6
Compressive strength	MPa	ISO 604	120 - 140
Hardness	Shore D	ISO 868	80 - 90
Glass transition temperature (DSC)	°C	ISO 11357 - 2	75 - 85
Water absorption 25°C / 24 hours	% w/w	ISO 62	Max 0.5

Packaging

Lapox ARL-125 is available in 30 kg, 110 kg and 240 kg carboys. Lapox AH-336 is available in 1 kg HDPE bottles. Other packing may be considered on request.

Storage and handling

Lapox ARL-125 and Lapox AH-336 have shelf-life of 2 years if stored in their original sealed containers. Resin and hardener may crystallise if stored below 15°C. Crystallisation may be reversed completely by heating the material between 60°C and 70°C. It is recommended to use resin and hardener only when they are clear and free from cloudiness. Both resin and hardener may cause irritation to sensitive skins. If contact does occur then it should be washed off immediately with soap and warm water. Please refer to the Safety Data Sheet (SDS) for detailed instructions on storage and handling.

Safety

Wear personal protective equipment (PPE). Avoid contact with the eyes and skin. In case of direct contact and irritation, the resin should be washed off immediately with soap and warm water. Avoid breathing vapours, mist or gas. Please refer to the SDS for detailed safety instructions.

Spills and disposal

In case of spills, sweep up and shovel the spilled material. Keep spilled material in suitable, closed containers for disposal. Soak up with an absorbent such as clay, sand or other suitable material. Flush area with water to remove trace residue. Do not allow the product to reach the sewage system. Waste must be disposed of in accordance with federal, state or local regulations, as applicable.

LAPOX[®] ARL-125 | AH-336

Technical Data Sheet | Polymers Business



Contact

E-mail: polymers@atul.co.in
Website: www.atul.co.in

Note

Lapox[®] is a registered trademark of Atul Ltd.

Manufacturing site

Atul 396 020, Gujarat, India
Telephone: (+91 2632) 230000 | 233261
E-mail: contact@atul.co.in

Disclaimer: The information contained herein is for information purposes only. While enough care is taken in disclosing the information, users of this information are advised to cross-check the same depending upon use | application. Atul Ltd does not give any assurance or warranty or guarantee in regard to the accuracy or completeness of the information and no claim or liability will be accepted or entertained in regard thereto. Atul Ltd makes no warranty of any kind, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose or performance or usage of trade.

LAPOX[®] ARL-125 | AH-336

Technical Data Sheet | Polymers Business

