

## Description

Polygrip HVAC CLASSIC is a high strength synthetic rubber based adhesive specially developed for various insulation requirements in HVAC and R segment. Polygrip HVAC CLASSIC has an excellent adhesion to variety of substrates like galvanised iron, aluminum, steel, nitrile rubber, glass wool and cross linked polyethylene to provide durable insulation requirements of HVAC and R applications.

## Advantages

- Excellent tack and tack retention time
- Excellent adhesion to variety of substrates
- Excellent coverage
- Excellent spreadability and ease of application
- Long lasting durable bond with excellent water resistance
- Mild smell
- No added benzene formulation

## Applications

**AC ducting and air ventilation system fabrications:** Bonding of nitrile rubber, cross linked polyethylene and glass wool to duct surfaces.

**Chilled water piping:** Bonding of nitrile rubber, cross linked polyethylene and glass wool to painted MS surface.

**Acoustic insulation:** Bonding of nitrile rubber, cross linked polyethylene to painted concrete surfaces | galvanised iron duct inner surface.

**Under deck Insulation:** Bonding of nitrile rubber and cross linked polyethylene to painted concrete surfaces.

## Typical specifications

Properties	Unit	Test method	Values
Appearance	-	Visual	Yellow viscous liquid
Density at 30°C	g/ml	-	0.82 - 0.86
Viscosity at 30°C	c Ps	ASTM D2196	1,050 - 1,500
Tack retention time <sup>1</sup>	Minutes	-	Max 30

<sup>1</sup>Tack retention time (open time) is generally measured after evaporation of solvent once adhesive applied in thin film. It may vary depending upon ambient temperature and humid conditions.

## Process of application

**Surface preparation:** Ensure that substrates to be bonded are clean, dry and free from oil, grease and foreign particles such as dust and rust.

**Application method:** Stir adhesive well and make it homogeneous prior to use. Apply adhesive uniformly in thin layer on both the substrates to be bonded with brush, spatula or any suitable tool. Allow evaporation of solvent from adhesive layer. The evaporation of solvent may take 5 minutes to 10 minutes, which depends upon ambient temperature and humidity. Assemble both the substrates with uniform contact pressure to achieve intimate contact without air pockets. The optimum bond strength is achieved after 24 hours.

## Packaging

Polygrip HVAC CLASSIC is available in 5 L and 30 L MS drums. Other packing may be considered on request.

# POLYGRIP® HVAC CLASSIC



Technical Data Sheet | Polymers Business

**Storage and handling** Polygrip HVAC CLASSIC should be stored in cool and dry place away from moisture, heat and direct sunlight. It contains highly volatile solvents, which will release during application, processing and use. These volatile solvents are highly flammable, hence adhesive must not come in contact with heat, spark and necked flame. This product has a shelf-life of 1 year if stored in its original container between 2°C and 40°C away from humidity and excessive heat. Please refer to the Safety Data Sheet (SDS) for detailed instructions on storage and handling.

**Safety** Wear personal protective equipment (PPE). Avoid contact with the eyes and skin. In case of direct contact and irritation, it should be washed off immediately with soap and warm water. Proper ventilation must be provided to shop floor where adhesive is used. Avoid breathing vapours, mist or gas. Please refer to the SDS for detailed safety instructions.

**Spills and disposal** In case of spills, sweep up and shovel the spilled material. Keep spilled material in suitable, closed containers for disposal. Soak up with an absorbent such as clay, sand or other suitable material. Flush area with water to remove trace residue. Do not allow the product to reach the sewage system. Waste must be disposed of in accordance with federal, state or local regulations, as applicable.

**Contact** E-mail: [support\\_polymers@atul.co.in](mailto:support_polymers@atul.co.in)  
Website: [www.atul.co.in](http://www.atul.co.in)

**Note** Polygrip® is a registered trademark of Atul Ltd.

**Manufacturing site**  
Atul 396 020, Gujarat, India  
Telephone: (+91 2632) 230000 | 233261  
E-mail: [contact@atul.co.in](mailto:contact@atul.co.in)

Disclaimer: The information contained herein is for information purposes only. While enough care is taken in disclosing the information, users of this information are advised to cross-check the same depending upon use | application. Atul Ltd does not give any assurance or warranty or guarantee in regard to the accuracy or completeness of the information and no claim or liability will be accepted or entertained in regard thereto. Atul Ltd makes no warranty of any kind, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose or performance or usage of trade.