

LAPOX[®] L-12 | AH-411

Technical Data Sheet | Polymers Business



Ambient cure epoxy system

Lapox L-12	100	pbw
Lapox AH-411	22	pbw

Description

Lapox L-12 is a liquid, unmodified epoxy resin of medium viscosity which can be used with various hardeners for making fiber reinforced composites parts and tools. Epoxy curing agent Lapox AH-411 is a low viscosity room temperature curing liquid hardener. This system gives a moderate pot life and rapid cure at ambient temperatures. System is recommended for high thermal stability and good chemical resistance.

Applications

FRP tools
Industrial and structural parts

Processing

Filament winding
Pultrusion
Resin transfer moulding of small parts
Wet lay-up

Typical specifications

Lapox L-12

Properties	Unit	Test method	Values
Appearance	-	Visual	Clear, viscous liquid
Colour	GS	ASTM D1544	Max 1
Viscosity at 25°C	m Pas	ASTM D2196	9,000 - 12,000
Epoxy content	Eq/kg	ASTM D1652	5.26 - 5.55
Specific gravity at 25°C	-	ASTM D792	1.1 - 1.2

Lapox AH-411

Properties	Unit	Test method	Values
Appearance	-	Visual	Clear liquid
Colour	GS	ASTM D1544	Max 1
Viscosity at 25°C	m Pas	ASTM D2196	10 - 20
Specific gravity at 25°C	-	ASTM D792	0.90 - 0.95

Processing properties

Properties	Unit	Test method	Values
Mixing ratio (by weight)	-	Visual	Resin: 100 Hardener: 22
Initial mix viscosity	m Pas	ASTM D2196	800 - 1,200 / 25°C
Pot life at 25°C	Minutes	ASTM D2471	90 - 120
Curing shrinkage	%	-	1.5
Curing schedule	°C / hours	-	80°C / 2 hours + 100°C / 2 hours + 120°C / 2 hours + 150°C / 4 hours

LAPOX[®] L-12 | AH-411

Technical Data Sheet | Polymers Business



Typical properties of neat cured system

Curing schedule: 80°C / 2 hours + 100°C / 2 hours + 120°C / 2 hours + 150°C / 4 hours
Determined on standard test specimen at 25°C

Properties	Unit	Test method	Values
Tensile strength	m Pa	ISO 527	60 - 70
Elongation at break	%	ISO 527	2 - 5
Elastic modulus in tension	g Pa	ISO 527	2.9 - 3.3
Flexural strength	m Pa	ISO 178	120 - 135
Flexural elongation at break	%	ISO 178	5 - 10
Elastic modulus in flexural	g Pa	ISO 178	2.9 - 3.3
Glass transition temperature (DSC)	°C	ISO 11357 - 2	140 - 155
Water absorption 25°C / 24 hours	% w/w	ISO 62	Max 0.17

Packaging

Lapox L-12 is available in 30 kg, 110 kg and 240 kg carboys. Lapox AH-411 is available in 1 kg HDPE bottles. Other packing may be considered on request.

Storage and handling

Lapox L-12 and hardener Lapox AH-411 have shelf-life of 2 years if stored in their original sealed containers. Resin and hardener may crystallise if stored below 15°C. Crystallisation may be reversed completely by heating the material between 60°C and 70°C. It is recommended to use resin and hardener only when they are clear and free from cloudiness. Hardener is sensitive to moisture. Container must be closed properly immediately after use. Both resin and hardener may cause irritation to sensitive skins. If contact does occur then it should be washed off immediately with soap and warm water, consult doctor immediately. Please refer to the Safety Data Sheet (SDS) for detailed instructions on storage and handling.

Safety

Wear personal protective equipment (PPE). Avoid contact with the eyes and skin. In case of direct contact and irritation, the resin should be washed off immediately with soap and warm water. Avoid breathing vapours, mist or gas. Please refer to the SDS for detailed safety instructions.

Spills and disposal

In case of spills, sweep up and shovel the spilled material. Keep spilled material in suitable, closed containers for disposal. Soak up with an absorbent such as clay, sand or other suitable material. Flush area with water to remove trace residue. Do not allow the product to reach the sewage system. Waste must be disposed of in accordance with federal, state or local regulations, as applicable.

Contact

E-mail: polymers@atul.co.in
Website: www.atul.co.in

Note

Lapox[®] is a registered trademark of Atul Ltd.

LAPOX[®] L-12 | AH-411

Technical Data Sheet | Polymers Business



Manufacturing site

Atul 396 020, Gujarat, India

Telephone: (+91 2632) 230000 | 233261

E-mail: contact@atul.co.in

Disclaimer: The information contained herein is for information purposes only. While enough care is taken in disclosing the information, users of this information are advised to cross-check the same depending upon use | application. Atul Ltd does not give any assurance or warranty or guarantee in regard to the accuracy or completeness of the information and no claim or liability will be accepted or entertained in regard thereto. Atul Ltd makes no warranty of any kind, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose or performance or usage of trade.