

**Description** Polygrip SP-9 is a sprayable synthetic rubber base adhesive. It is specially designed to provide long tack retention time (open time), suitable for bonding large components. It is recommended for bonding variety of substrates like foam to foam, foam to painted metal, foam to mild steel, rexine, fiber reinforced plastics (FRP), PVC foam, wood, rexine, and fabric and non-woven carpet. The bonds are resistant up to 70°C.

**Advantages**

- Long tack retention time
- Suitable for large bonding area
- Higher coverage
- Mild smell
- No harmful benzene
- Rapid strength development

**Applications**

- AC ducting
- Automobile (roof lining, door trim, non-woven carpets)
- Generator canopy
- Luggage
- Sofa, mattress and chairs manufacturing
- Upholstery fixing and seat making

Typical specifications	Properties	Unit	Test method	Values
	Appearance	-	Visual	Light yellow to brown
	Density at 30°C	g/ml	-	0.78 - 0.85
	Viscosity at 30°C	cPs	ASTM D2196	100 - 200
	Tack retention time <sup>1</sup>	Minutes	-	Min 30

<sup>1</sup>Tack retention time (open time) is generally measured after evaporation of solvent once adhesive applied in thin film. It may vary depending upon ambient temperature & humidity conditions.

**Process of application** **Surface preparation:** Ensure that substrates to be bonded are clean, dry and free from oil, grease and foreign particles such as dust and rust.

**Application:** Stir adhesive well and make it homogeneous prior to use. Spray the adhesive by using air supported gun (make-pilot) having orifice diameter of 1.5 mm to 2.0 mm at air pressure of 45 psi to 55 psi. The adhesive to be applied on both the substrates to be bonded. Allow evaporation of solvents for 1 to 2 minutes. Assemble both the substrates with uniform contact pressure to achieve intimate contact without air pockets. The optimum bond strength is achieved after 24 hours.

**Packaging** Polygrip SPR is available in 30 L metal drums. Other packing may be considered on request.

**Storage and handling** Polygrip SPR should be stored in cool and dry place away from moisture, heat and direct sunlight. It contains highly volatile solvents, which will release during application, processing and use. These volatile solvents are highly flammable, hence adhesive must not come in contact with heat, spark and necked flame. This product has a shelf-life of 1 year, if stored in its original container between 2°C and 40°C away from humidity and excessive heat. Please refer to the Safety Data Sheet (SDS) for detailed instructions on storage and handling.

**Safety** Wear personal protective equipment (PPE). Avoid contact with the eyes and skin. In case of direct contact and irritation, it should be washed off immediately with soap and warm water. Proper ventilation must be provided to shop floor where adhesive is used. Avoid breathing vapours, mist or gas. Please refer to the Safety Data Sheet (SDS) of Polygrip SPR for detailed safety instructions.

# POLYGRIP® SP-9

Technical Data Sheet | Polymers Business



## Spills and disposal

In case of spills, sweep up and shovel the spilled material. Keep spilled material in suitable, closed containers for disposal. Soak up with an absorbent such as clay, sand or other suitable material. Flush area with water to remove trace residue. Do not allow the product to reach the sewage system. Waste must be disposed of in accordance with federal, state or local regulations, as applicable.

## Contact

E-mail: [support\\_polymers@atul.co.in](mailto:support_polymers@atul.co.in)

Website: [www.atul.co.in](http://www.atul.co.in)

## Note

Polygrip® is a registered trademark of Atul Ltd.

## Manufacturing site

Atul 396 020, Gujarat, India

Telephone: (+91 2632) 230000 | 233261

E-mail: [contact@atul.co.in](mailto:contact@atul.co.in)

Disclaimer: The information contained herein is for information purposes only. While enough care is taken in disclosing the information, users of this information are advised to cross-check the same depending upon use | application. Atul Ltd does not give any assurance or warranty or guarantee in regard to the accuracy or completeness of the information and no claim or liability will be accepted or entertained in regard thereto. Atul Ltd makes no warranty of any kind, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose or performance or usage of trade.

December 2020

Page 2 of 2